



# PPG LO-VEL<sup>®</sup> 6200

## Flatting Agent – Non-Treated

COATINGS

PPG LO-VEL<sup>®</sup> 6200 silica is a synthetic amorphous silicon dioxide flatting agent designed for use where a Hegman value of 6.5 is required. A combination of high flatting efficiency, narrow particle size distribution, ease of dispersion and resistance-to-settling makes this product ideal for overprint varnish and other non-pigmented finishes where clarity, uniformity and smoothness are essential.

### Benefits

- High flatting efficiency at a Hegman range of 6 to 7
- Strong resistance-to-settling
- Designed for use in solvent, water-based, clear and pigmented coatings
- Provides easy dispersion, leveling and smooth finish
- Resistant to over-grind
- Excellent color stability and color match
- Designed for use in one-step and flatting concentrate processes



### Applications

- Overprint varnishes
- Printing inks
- Wood coatings
- Appliance finishes
- Aircraft coatings
- Metal furniture finishes
- Vinyl fabric lacquers



Lo-Vel 6200 Silica – Typical Properties	
Median Particle Size (laser light diffraction), $\mu\text{m}$	7
$\text{N}_2$ -BET Surface Area, $\text{m}^2/\text{g}$	700
DOA-Oil Absorption Number, $\text{mL}/100\text{g}$	265
Hegman Value	6.5
Fineness of Grind, $\mu\text{m}$	20
Moisture Content, %	$\leq 5.0$
pH	6.5

# PPG LO-VEL® 6200

Flatting Agent – Non-Treated

COATINGS

## Samples

Samples are available per request from customer service.

## Packaging

Standard packaging in small bags are unitized for shipping on pallets and stretch wrapped with clear plastic film. Please consult with customer service or your sales representative regarding additional packaging options including custom package sizes.

## Storage

To ensure product integrity, we recommend that our silica products be stored under dry, clean conditions, protected against exposure to direct sunlight and other substances, and used within 12 months of the date of manufacture. PPG silica products that are stored for more than one year from the date of manufacture should be tested for moisture content.

## Safety and Health Effects

We recommend that, before use, anyone using or handling this product thoroughly read and understand the information and precautions on the label, as well as in other product safety publications such as the Safety Data Sheet. Any health hazard and safety information contained herein should be passed on to your customers or employees, as the case may be. The products mentioned herein can be hazardous if not used properly. Like all potentially hazardous materials, this product must be kept out of the reach of children.

## Product Safety and Regulatory Information

For the latest product safety and regulatory information, please reference the Safety Data Sheets at [www.ppgsilica.com](http://www.ppgsilica.com).



**USA**  
PPG Silica Products  
440 College Park Drive  
Monroeville, PA 15146 USA

Customer Service: 1-800-243-6745  
Technical Service: 1-800-764-7369  
E-mail: [silicacustserv@ppg.com](mailto:silicacustserv@ppg.com)

**EUROPE**  
PPG Delfzijl Plant  
P.O. Box 181  
9930 AD Delfzijl, The Netherlands

Customer Service: +31-596-676710  
Technical Service: +31-596-676710  
E-mail: [csdelfzijl@ppg.com](mailto:csdelfzijl@ppg.com)

