

COATINGS

PPG LO-VEL® 2018 flatting agent is a synthetic amorphous silicon dioxide, wax-treated flatting agent designed to reduce the gloss of radiation cured coatings and with performance similar to silica gels in radiation cured coating formulations.

Benefits

- Resists over grind and offers greater flatting efficiency than conventional precipitated silica flatting agents
- Can be easily incorporated and dispersed in different coatings systems
- Provides excellent coating storage stability and good resistance to hard settling in most coatings systems

Lo-Vel 2018 Silica — Typical Properties	
Median Particle Size (laser light diffraction), µm	12.5
N ₂ -BET Surface Area, m ² /g	160
DOA-Oil Absorption Number, mL/100g	265
Hegman Value	5.5
Fineness of Grind, µm	32
Moisture Content, %	≤5
рН	6.7



Applications
Wood Flooring
Furniture laminates
Beverage Cans



Samples

Samples are available per request from customer service.

Packaging

Standard packaging in small bags are unitized for shipping on pallets and stretch wrapped with clear plastic film. Please consult with customer service or your sales representative regarding additional packaging options including custom package sizes.

Storage

To ensure product integrity, we recommend that our silica products be stored under dry, clean conditions, protected against exposure to direct sunlight and other substances, and used within 12 months of the date of manufacture. PPG silica products that are stored for more than one year from the date of manufacture should be tested for moisture content.

Safety and Health Effects

We recommend that, before use, anyone using or handling this product thoroughly read and understand the information and precautions on the label, as well as in other product safety publications such as the Safety Data Sheet. Any health hazard and safety information contained herein should be passed on to your customers or employees, as the case may be. The products mentioned herein can be hazardous if not used properly. Like all potentially hazardous materials, this product must be kept out of the reach of children.

Product Safety and Regulatory Information

For the latest product safety and regulatory information, please reference the Safety Data Sheets at www.ppgsilica.com.



USA PPG Silica Products 440 College Park Drive Monroeville, PA 15146 USA

Customer Service: 1-800-243-6745 Technical Service: 1-800-764-7369 E-mail: silicacustserv@ppg.com EUROPE
PPG Delfzijl Plant
P.O. Box 181
9930 AD Delfzijl, The Netherlands

Customer Service: +31-596-676710 Technical Service: +31-596-676710 E-mail: csdelfzijl@ppg.com

